


## WHITE OPAQUE CPP FILM

### CAPP - WS



#### PRODUCT DESCRIPTION

CAPP-WS is a co-extruded, one side heat sealable, one side treated, solid white cast polypropylene (CPP) film

#### PRODUCT FEATURES

- Good sealing integrity & Hot tack
- Good performance on HFFS & VFFS machine

#### APPLICATIONS

- Lamination & Conversion for confectionary Packaging
- Biscuit and snacks packaging

| PROPERTIES                          |         | UNIT    | TEST METHOD | CAPP - WS   |      |      |      |
|-------------------------------------|---------|---------|-------------|-------------|------|------|------|
| Nominal Thickness (5%)              |         | μ       | D-374       | 22          | 25   | 30   | 40   |
| Grammage (5%)                       |         | gm/ m²  | CPFTM       | 20.9        | 23.8 | 28.5 | 38   |
| Yield                               |         | m²/kg   |             | 47.8        | 42   | 35.1 | 26.3 |
| MECHANICAL PROPERTIES               |         |         |             |             |      |      |      |
| Tensile strength                    | MD      | Kg/cm²  | D-882       | 500 – 700   |      |      |      |
|                                     | TD      |         |             | 180 – 280   |      |      |      |
| Elongation at Break                 | MD      | %       |             | 500 - 600   |      |      |      |
|                                     | TD      |         |             | 600 - 800   |      |      |      |
| THERMAL PROPERTIES                  |         |         |             |             |      |      |      |
| Seal initiation temperature (±3 °C) | NT Side | °C      | CPFTM       | 115         |      |      |      |
| Sealing Strength                    | NT Side | gm/25mm | CPFTM       | 1400 - 1800 |      |      |      |
| SURFACE PROPERTIES                  |         |         |             |             |      |      |      |
| Coefficient of Friction             | NT Side | Kinetic | D-1894      | 0.30 – 0.50 |      |      |      |
| Surface Tension (Min.)              |         | dyne/cm | D-2578      | 38          |      |      |      |
| OPTICAL PROPERTIES                  |         |         |             |             |      |      |      |
| Opacity                             |         | %       | CPFTM       | 55 - 65     |      |      |      |
| BARRIER PROPERTIES                  |         |         |             |             |      |      |      |

#### FOOD CONTACT

CPF - CPP products complies with EC and FDA regulations. Specific documents and MSDS are available upon request.

#### STORE & HANDLING

A storage temperature below 30°C & humidity 55±5% is recommended to avoid any deterioration of the film surface properties. Excess humidity and heat can cause problem such as fast treatment decay, which can affect the quality of printing and coating. It is advisable to use material on FIFO basis.

#### DISCLAIMER

The property given in the technical data sheet do not constitute product specification but represent typical performance values based on the best of our knowledge and believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Chiripal Poly film does not guarantee the typical values. Chiripal Poly reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information.