

Soft Pharma Bare (PB) CFPBS 20-40mic

		OILFI	iaiiiia	Daie (, רט)	, FF D	3 ZU-	4011111	_		
Parameter	rs	Spec	cifications	3							
Foil Temper		Soft (O Temper)									
Alloy		AA8011									
Width		Standard (± 1 mm)									
Foil Thickness Range		0.020 to 0.050 mm									
Foil Thickness Tolerance		+/- 5 %									
		Thicknes	s (mm)	Alloy	,	Tem	per	UTS	(MPa)	%	Elongation
		0.0	2	8011/80	079	0)	60	-100		≥ 1
Mechanical Properties		0.025 8011/8079			079	0	0 60		- 100		≥ 2
		0.0	0.03 8011/8079			0)	60	60 - 100 ≥ 2		≥ 2
		0.0	0.04 8011/8079			0)	60	60 - 100 ≥ 2		
		0.05 8011/8079			079	0		60	- 100		≥ 2
Pinhole Count		Thickness (mm)						Pinhole count per sq m.			
		0.021						max			
		0.025						Nil			
		0.03						Nil			
		0.04 Nil									
Wettability (Dyne/cm)		72 / Index - A (For Soft Foil)									
Free fall		1.5 Mtr. (Maximum)									
Reel OD (mm)		500 to 800									
Core ID (mm)		152.4 (± 0.5 mm)									
Type of Core		Steel									
Winding uniformity		± 0.5 mm edge wandering (Max)									
Winding		BSO/DSO (As per customer requirement)									
Surface		Shall be clean and free from scratches, wrinkles, cracks or other internal defects									
Splice		Shall be made of smooth ultrasonic welding throughout the web width									
		Average number of splices per roll shall not exceed two per roll.									
Number of Splice:		70 % Joint free,									
		20 % with one joint									
		10 % with two joints									
Identification		Label on individual roll indicating Reel No., Thickness, Width, Surface, No. of									
		joints, Net weight, Gross weight.									
Packing		Rolls are packed in export worthy packing. Each roll individually packed & placed in wooden having exponeded position.									
Otorono		in wooden box in suspended position. Storage must be in packed condition to avoided direct moisture and dust contact.									
Storage		1									
		The storage area must be cool and dry with a lower relative humidity and lower temperature variation									
·											
Chemical Composition											
Alloy	Standard	Si	Fe	Cu	Mn	Mg	Zn	Ti	Oth		Al
	A ====================================				_				Ind.	Total	
AA8011	As per EN573-3	0.40-	0.5-1.0	0.1	0.1	0.1	0.1	0.05	-	≤0.15	Remainder
1.105=5		0.80		Max	Max	Max	Max	Max		0.05	
A A8079	As per EN573-3	0.05-	0.30	0.7-1.3	0.05	-	-	0.1	-	≤0.05	≤0.15
					Max			Max			