



CHEMICAL COATED BOPET FILM

PRODUCT DESCRIPTION

Chiripal Poly Films CPT50 is **Biaxially Oriented Transparent** Polyester film with inside chemical coated and outside Plain. Chemical coated side is suitable for Printing and Metallizing This is also available with outside chemical coated and inside plain

FEATURES

- Excellent stiffness & mechanical properties
- Chemical coatingside enhances the Metal adhesion and resulting a good laminate bond strength
- Excellent transparency and surface properties.
- Excellent machine ability & dimensional stability over a wide range of temperature.

APPLICATION

▶ This is suitable for Metallization and used for various high performance application like Hot fills, aggressive liquid packaging, Aseptic packaging

PROPERTIES		UNIT	TEST METHOD	CP08T50	CP10T50	CP12T50
Nominal Thickness		Micron	Internal	8	10	12
		Gauge	Method	32	40	48
Yield		m²/kg		89.2	71.4	59.6
MECHANICAL PROP	ERTIES (Mi	n)				
Tensile Strength	MD		ASTM	2200	2200	2200
	TD	kg/cm ²	D-882	2100	2100	2100
Elongation Break	MD		ASTM	100	100	100
	TD	%	D-882	90	90	90
THERMAL PROPERT	TIES (Max)					
Thermal	MD			2.4	2.4	2.4
Shrinkage		%	ASTM			
(at 150°C /30 mins)	TD		D-1204	0.4	0.4	0.4
SURFACE PROPERT	IES (Max)					
COF	Static		ASTM	0.48	0.48	0.48
(Film to Film)	Dynamic	-	D-1894	0.42	0.42	0.42
SURFACE TENSION	<u>'</u>					
Plain Side			ASTM	52	52	52
		Dyne/cm	D-2578			
Coated Side				52	52	52
OPTICAL PROPERTI	ES					
Haze (Max)			ASTM			
		%	D-1003	3.0	3.0	3.0
Light Transmission			ASTM			
			D-1003	88	88	88
BARRIER PROPERT						
WVTR, 37.7°C, 90% RH		gm/m²	ASTM F-	40	40	40
		/day	1249			
02 Permeability 23°C, 0%RH		cm ³ /m ²	ASTM D-			
		/day	3985-95	130	130	130

Note: MD - Machine Direction, TD - Transverse Direction, COF - Co-efficient of Friction

DISCLAIMER: The property given in the present technical data sheet does not constitute product specification but represents typical performance values based on the best of our knowledge and believed to be accurate. These are given in good faith, and the Customer is requested to satisfy its suitability for its particular purpose. The user is solely responsible for the end-use of the product and needs to perform tests to confirm the product suitability/compatibility in all respects. Chiripal Poly Films does not guarantee typical values and reserves the right to change the technical datasheet anytime required to enhance the quality of the products without prior information.