



CHEMICAL COATED BOPET FILM

PRODUCT DESCRIPTION

Chiripal Poly Films CPT51 is Biaxially Oriented Transparent Polyester film with Inside chemical coated and Outside Corona treated. This film is also available with Inside Corona treatment and Outside chemical coated

FEATURES

- ▶ Excellent stiffness & mechanical properties.
- ▶ Chemical coating side enhances the ink adhesion in printing, and resulting a good laminate bond strength
- ▶ Excellent transparency and surface properties.
- ▶ Excellent machine ability & dimensional stability over a wide range of temperature.

APPLICATION

- ▶ This is suitable for Metallization and used for various high performance application like Hot fills, aggressive liquid packaging, Aseptic packaging

PROPERTIES		UNIT	TEST METHOD	CP08T51	CP10T51	CP12T51
Nominal Thickness		Micron	Internal Method	8	10	12
		Gauge		32	40	48
Yield		m²/kg		89.2	71.4	59.6
MECHANICAL PROPERTIES (Min)						
Tensile Strength	MD	kg/cm²	ASTM	2200	2200	2200
	TD		D-882	2100	2100	2100
Elongation Break	MD	%	ASTM	100	100	100
	TD		D-882	90	90	90
THERMAL PROPERTIES (Max)						
Thermal Shrinkage (at 150°C /30 mins)	MD	%	ASTM D-1204	2.4	2.4	2.4
	TD			0.4	0.4	0.4
SURFACE PROPERTIES (Max)						
COF (Film to Film)	Static	-	ASTM D-1894	0.48	0.48	0.48
	Dynamic			0.42	0.42	0.42
SURFACE TENSION						
Coated Side		Dyne/cm	ASTM D-2578	52	52	52
Corona Treated Side				54	54	54
OPTICAL PROPERTIES						
Haze (Max)		%	ASTM D-1003	3.0	3.0	3.0
Light Transmission			ASTM D-1003	88	88	88
BARRIER PROPERTIES						
WVTR, 37.7 ^o C, 90% RH		gm/m² /day	ASTM F-1249	40	40	40
O2 Permeability 23 ^o C, 0%RH		cm³/m² /day	ASTM D-3985-95	130	130	130

Note : MD – Machine Direction, TD – Transverse Direction, COF - Co-efficient of Friction

DISCLAIMER: The property given in the present technical data sheet does not constitute product specification but represents typical performance values based on the best of our knowledge and believed to be accurate. These are given in good faith, and the Customer is requested to satisfy its suitability for its particular purpose. The user is solely responsible for the end-use of the product and needs to perform tests to confirm the product suitability/compatibility in all respects. Chiripal Poly Films does not guarantee typical values and reserves the right to change the technical datasheet anytime required to enhance the quality of the products without prior information.