



PRODUCT DESCRIPTION

Chiripal Poly Films CPW17 is Biaxially Oriented Transparent Polyester film with inside side corona and outside Antistatic coating .Corona side is suitable for Printing.

This film is also available with inside coating and outside Corona

FEATURES

- Good clarity and transparency
- Good adhesion to inks
- Excellent twistability and dead fold retention ability
- Suitable for high speed candy machine

APPLICATION

- Twist wrap for Chocolate, lollipop,etc
- Gift wrapping

CHEMICAL COATED BOPET FILM

PROPERTIES		UNIT	TEST METHOD	CP15W71	CP18W71	CP23W71
Nominal Thickness		Micron	Internal Method	15	18	23
		Gauge		60	72	92
Yield		m²/kg		47.6	39.6	31.1
MECHANICAL PROPERTIES (Min)						
Tensile Strength	MD	kg/cm²	ASTM	2300	2400	2400
	TD		D-882	2400	2500	2500
Elongation Break	MD	%	ASTM	110	110	110
	TD		D-882	100	100	100
THERMAL PROPERTIES (Max)						
Thermal Shrinkage (at 150°C /30 mins)	MD	%	ASTM D-1204	25	25	25
	TD			25	25	25
SURFACE PROPERTIES (Max)						
COF (Film to Film)	Static	-	ASTM	0.45	0.45	0.45
	Dynamic		D-1894	0.40	0.40	0.40
SURFACE TENSION						
Corona Side		Dyne/cm	ASTM D-2578	54	54	54
Coated Side				48	48	48
OPTICAL PROPERTIES						
Haze (Max)		%	ASTM D-1003	3.5	4.0	4.0
Light Transmission			ASTM D-1003	88	88	88
OTHER PROPERTIES						
Twist Ability		-	Internal Method	Excellent	Excellent	Excellent
Dead For Fold Abiliytcm³/m²						
BARRIER PROPERTIES						
WVTR, 37.7°C, 90% RH		gm/m² /day	ASTM F-1249	40	40	40
O2 Permeability 23°C, 0%RH		cm³/m² /day	ASTM D-3985-95	130	130	130

Note : MD – Machine Direction, TD – Transverse Direction, COF - Co-efficient of Friction

DISCLAIMER: The property given in the present technical data sheet does not constitute product specification but represents typical performance values based on the best of our knowledge and believed to be accurate. These are given in good faith, and the Customer is requested to satisfy its suitability for its particular purpose. The user is solely responsible for the end-use of the product and needs to perform tests to confirm the product suitability/compatibility in all respects. Chiripal Poly Films does not guarantee typical values and reserves the right to change the technical datasheet anytime required to enhance the quality of the products without prior information.