



CP-FSR4

FILM GRADE SILICA POLYESTER CHIPS

PRODUCT FEATURES AND APPLICATION

CP-FSR4 is film grade Silica polyester chips. It is suitable for manufacturing of polyester films for flexible packaging as well as industrial applications. This chip contains 4000 ppm of Silica

TEST PARAMETERS		UNIT	TEST METHOD	TYPICAL VALUE
Intrinsic Viscosity		dl/gm	CPQA/WI/30	0.64±0.02
End Group (COOH)		Meq/kg	CPQA/WI/32	<35
DEG		%	CPQA/WI/52	1.1±0.2
Melting Point		Deg C	CPQA/WI/36	256±2
Color	L	Hunter	CPQA/WI/37	>60
	b	Hunter	CPQA/WI/37	<9
Ash		%	CPQA/WI/38	0.40±0.02
Moisture content (When packed)		%	CPQA/WI/41	<0.25
Chip/gm		Nos	CPQA/WI/50	30±5

FOOD CONTACT

CP-FSR4 complies with EC and FDA regulations.

STORAGE & HANDLING

Recommended to store at temperature below 30°C & humidity 55±5 %

DISCLAIMER

The property given in this technical data sheet does not constitute product specifications but represents typical performance values based on the best of our knowledge and believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Chiripal Polyfilm does not guarantee the typical values and reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information.

Manufactured by.:



Corporate Office: Chiripal House Shivranjani Cross Road Satellite, Ahmedabad-380015 India
www.chiripalpolyfilms.in petresin.marketing@chiripalgroup.com