



ISOTROPIC BOPET FILM

PRODUCT DESCRIPTION

Chiripal Poly Films CP100 is Biaxially Oriented Tranaparent Polyester film with both sides plain.

This film is Isotropic in nature

FEATURES

- Excellent Isotropic Characteristics
- Excellent stiffness & mechanical properties.
- Excellent transparency and surface properties
- Excellent machine ability & dimensional stability over a wide range of temperature.

APPLICATION

Used For Iidding Application

PROPERTIES		UNIT	TEST METHOD	CP08I00	CP10I00	CP12I00
Nominal Thickness		Micron	Internal	8	10	12
		Gauge	Method	32	40	48
Yield		m²/kg		89.2	71.4	59.6
MECHANICAL PROP	ERTIES (Mi	n)				
Tensile Strength	MD		ASTM	2300	2300	2300
	TD	kg/cm ²	D-882	2300	2300	2300
Elongation Break	MD		ASTM	100	100	100
	TD	%	D-882	90	90	90
HERMAL PROPERT	IES (Max)					
Thermal	MD			2.4	2.4	2.4
Shrinkage		%	ASTM			
(at 150°C /30 mins)	TD		D-1204	0.4	0.4	0.4
URFACE PROPERT	IES (Max)					
COF	Static		ASTM	0.48	0.48	0.48
(Film to Film)	Dynamic	-	D-1894	0.42	0.42	0.42
URFACE TENSION						
Plain Side		Dyne/cm	ASTM D-2578	44	44	44
PTICAL PROPERTI	FS	,				
Haze (Max)			ASTM			
, ,		%	D-1003	3.0	3.0	3.0
Light Transmission			ASTM			
3			D-1003	88	88	88
ARRIER PROPERTI	FS					
WVTR, 37.7°C, 90% RH		gm/m²	ASTM F-	40	40	40
		/day	1249			
02 Permeability 23°C, 0%RH		cm ³ /m ²	ASTM D-			
	-,	/day	3985-95	130	130	130

DISCLAIMER: The property given in the present technical data sheet does not constitute product specification but represents typical performance values based on the best of our knowledge and believed to be accurate. These are given in good faith, and the Customer is requested to satisfy its suitability for its particular purpose. The user is solely responsible for the end-use of the product and needs to perform tests to confirm the product suitability/compatibility in all respects. Chiripal Poly Films does not guarantee typical values and reserves the right to change the technical datasheet anytime required to enhance the quality of the products without prior information.